

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Presented) An over-coating composition for coating a photoresist composition to provide a vertical photoresist pattern, said over-coating composition comprising (a) an over-coating resin derived from poly(acrylic acid / methyl acrylate), (b) a solvent, and (c) a basic compound.

2. (Original) The over-coating composition according to claim 1, wherein said over-coating resin is a water-soluble polymer.


3. Cancelled.

4. (Original) The over-coating composition according to claim 1, wherein pKa of the conjugate acid of said basic compound is about 13 or less.

5. (Original) The over-coating composition according to claim 1, wherein said basic compound is a nitrogen containing compound.

6. (Previously Presented) The over-coating composition according to Claim 1, wherein said basic compound is selected from the group consisting of an amine compound and a hydroxide salt thereof; an amide compound; a urethane compound; and a mixture thereof.

7. (Original) The over-coating composition according to claim 6, wherein said amine compound is of the formula:



wherein each of R₁, R₂ and R₃ is independently H, or C₁-C₂₀ alkyl.

8. (Original) The over-coating composition according to claim 7, wherein said alkyl is selected from the group consisting of unsubstituted C₁-C₂₀ alkyl, C₁-C₂₀ hydroxyalkyl, C₁-C₂₀ alkyl carboxylic acid, C₁-C₂₀ aminoalkyl, C₁-C₂₀ alkylketone, and C₁-C₂₀ alkylester.

9. (Original) The over-coating composition according to claim 6, wherein said amine compound is selected from the group consisting of L-proline, a tetraalkylammonium hydroxide salt, a tri(hydroxyalkyl)amine, and a mixture thereof.

10. (Original) The over-coating composition according to claim 9, wherein said tetraalkylammonium hydroxide salt is selected from the group consisting of tetramethylammonium hydroxide and tetramethylammonium hydroxide pentahydrate.

11. (Original) The over-coating composition according to claim 9, wherein said tri(hydroxyalkyl)amine is triethanolamine.

12. (Original) The over-coating composition according to claim 1, wherein the amount of said basic compound is in the range from about 0.001 to about 0.1 mol% of said solvent.

13. (Original) The over-coating composition according to claim 1, wherein the amount of said solvent is in the range from about 1000 to about 7000% by weight of said over-coating resin.

14.-21. Canceled

22. (Previously Presented) A composition for over-coating a photoresist layer used in a photolithography process wherein exposure of the photoresist to light of a particular wavelength generates acid from a photoacid generator present in the photoresist, said over-coating composition comprising (a) an over-coating resin derived from a mixture of acrylic

acid and an alkyl acrylate, (b) a solvent, and (c) a basic compound in an amount sufficient to diffuse into the underlying photoresist layer and neutralize at least a portion of the acid generated in the upper portion thereof.

23. (Previously Presented) The over-coating composition according to claim 22 wherein the amount of said basic compound is in the range from about 0.001 to about 0.1 mol% of said solvent.

24. (New) A process for forming a photoresist pattern, comprising the steps of:

- (a) coating a photoresist composition on a substrate to form a photoresist film;
- (b) coating an over-coating composition of claim 1 on the upper portion of said photoresist film to form a over-coating;
- (c) exposing said over-coated substrate to light using a light source; and
- (d) developing said exposed over-coated substrate.

25. (New) The process according to claim 24, wherein said photoresist composition comprises a chemically amplified photoresist resin.

26. (New) The process according to claim 25, wherein said chemically amplified photoresist resin is poly(tert-butyl bicyclo[2.2.1]hept-5-ene-2-carboxylate / 2-hydroxyethyl bicyclo[2.2.1]hept-5-ene-2-carboxylate / bicyclo[2.2.1]hept-5-ene-2-carboxylic acid / maleic anhydride).

27. (New) The process according to claim 24 further comprising a baking step before and/or after said exposure step (c).

28. (New) The process according to claim 27, wherein said baking step is performed at a temperature range of from 10 to 200°C.

Appl. No. 09/728,535

PATENT

Amdt. dated February 11, 2004

Amendment under 37 CFR 1.116 Expedited Procedure

Examining Group

29. (New) The process according to claim 24, wherein said light source is
ArF, KrF, F₂, EUV, E-beam, X-ray or ion beam.